



# RESINA FLESSIBILE

## RESINA Flessibile

	Green	Postcured	Method
<b>Mechanical Properties</b>			
Ultimate Tensile Strength	3.3 - 3.4 MPa	7.7 - 8.5 MPa	ASTM D 412-06
Elongation at Failure	60 %	75 - 85 %	ASTM D 412-06
Compression set	0.40 %	0.40 %	ASTM D 395-03
Tear Strength	9.5 - 9.6 kN/m	13.3 - 14.1 kN/m	ASTM D 624-00
Shore Hardness	70 - 75 A	80 - 85 A	ASTM 2240
<b>Thermal Properties</b>			
Vicat softening point	231 °C	230 °C	ASTM D 1525-09